



TECHNISCHES DATENBLATT		Ausgabe	
<i>TECHNICAL DATA SHEET</i>		<i>Edition</i>	
		<i>Jan. 10</i>	
		0799 - CPD GGR	
Produktname <i>Product trade name</i>		Sympaforce® 200 / 30 - 15 N	
Produkt-Ident <i>Product-ID-No.</i>		GELN20030	Farbcode: orange + violett <i>colour code: orange + violet</i>
Textiltyp <i>Textile type</i>	Polymer	MD PET Polyester high tenacity	
Ausrüstung <i>Coating type</i>		CMD PET Polyester high tenacity	
Farbe <i>Colour</i>		PVC <i>PVC</i>	
Schmelzpunkt <i>Melting point</i>	°C	PET 250-260	
Vliesstoff <i>Non-Woven</i>	g/m ²	kein <i>none</i>	
Gitteröffnung <i>Aperture size</i>	mm	MD 15 (± 2,0) CMD 15 (± 2,0)	
Höchstzugkraft <i>Tensile strength at max load</i>	kN/m	MD 225 (- 25,0) CMD 35 (- 5,0)	DIN EN ISO 10319
Dehnung <i>Elongation</i>	%	MD 11 (± 3,0) CMD 12 (± 3,0)	DIN EN ISO 10319
Übliche Bezugskraft <i>Usual force at strain</i>	kN/m	@ 2% 3% 5% 10% MD 43 54 66 147 CMD 6 7 10 22	
Flächengewicht <i>Mass per unit area</i>	g/m ²	800 (± 64)	DIN EN ISO 9864
Rollenmasse <i>Roll dimensions</i>	±10%	Breite Länge Gewicht <i>width length weight</i> 2,34 m 100 m 199 kg	
Vorgesehene Funktion <i>Intended use</i>	R	Bewehrung von Erdbauwerken <i>Soil reinforcement</i>	

Standard tolerances and technical developing change reserved
 The latest version of all Technical Data Sheets is available at www.synteen.de.