



<b>TECHNISCHES DATENBLATT</b>		Ausgabe	
<i>TECHNICAL DATA SHEET</i>		<i>Edition</i>	
		<i>Jan. 10</i>	
		<b>0799 - CPD GGR</b>	
<b>Produktname</b> <i>Product trade name</i>		<b>Sympaforce®</b>	
<b>Produkt-Ident</b> <i>Product-ID-No.</i>		<b>50 / 20 - 20 N</b>	
<b>Textiltyp</b> <i>Textile type</i>		<b>GELN05020</b> <b>Farbcode: weiß + orange</b> <i>colour code: white + orange</i>	
<b>Ausrüstung</b> <i>Coating type</i>	Polymer	MD <b>PET</b> Polyester high tenacity	
<b>Farbe</b> <i>Colour</i>		CMD <b>PET</b> Polyester high tenacity	
<b>Schmelzpunkt</b> <i>Melting point</i>		<b>PVC</b> <i>PVC</i>	
<b>Vliesstoff</b> <i>Non-Woven</i>	C	<b>schwarz</b> <i>black</i>	
<b>Gitteröffnung</b> <i>Aperture size</i>		PET <b>250-260</b>	
<b>Höchstzugkraft</b> <i>Tensile strength at max load</i>	g/m <sup>2</sup>	<b>kein</b> <i>none</i>	
<b>Dehnung</b> <i>Elongation</i>		MD 20 (± 3,0) CMD 20 (± 3,0)	
<b>Übliche Bezugskraft</b> <i>Usual force at strain</i>	mm	MD 59 (- 9,0)	DIN EN ISO 10319
<b>Flächengewicht</b> <i>Mass per unit area</i>		CMD 28 (- 8,0)	
<b>Rollenmasse</b> <i>Roll dimensions</i>	kN/m	MD 11 (± 3,0)	DIN EN ISO 10319
<b>Vorgesehene Funktion</b> <i>Intended use</i>		CMD 12 (± 3,0)	
	%	@ 2%    3%    5%    10%	
		MD 13    17    22    50	
	kN/m	CMD 4    5    6    17	
		275 (± 22)	DIN EN ISO 9864
	g/m <sup>2</sup>	<b>Breite</b> <b>Länge</b> <b>Gewicht</b>	
		<i>width</i> <i>length</i> <i>weight</i>	
	±10%	5,00 m    100 m    160 kg	
		<b>Bewehrung von Erdbauwerken</b>	
	R	<i>Soil reinforcement</i>	
		<b>Standard tolerances and technical developing change reserved</b>	
	<b>The latest version of all Technical Data Sheets is available at <a href="http://www.synteen.de">www.synteen.de</a>.</b>		