



TECHNISCHES DATENBLATT		Ausgabe	
<i>TECHNICAL DATA SHEET</i>		<i>Edition</i>	
		<i>Jan. 10</i>	
		0799 - CPD GGR	
Produktname <i>Product trade name</i>		Sympaforce®	
Produkt-Ident <i>Product-ID-No.</i>		50 / 50 - 20 N	
Textiltyp <i>Textile type</i>		GELN05050 Farbcode: weiß + violett <i>colour code: white + violet</i>	
Ausrüstung <i>Coating type</i>	Polymer	MD PET Polyester high tenacity	
Farbe <i>Colour</i>		CMD PET Polyester high tenacity	
Schmelzpunkt <i>Melting point</i>		PVC <i>PVC</i>	
Vliesstoff <i>Non-Woven</i>	C	schwarz <i>black</i>	
Gitteröffnung <i>Aperture size</i>	g/m ²	PET 250-260	
Höchstzugkraft <i>Tensile strength at max load</i>	mm	kein <i>none</i>	
Dehnung <i>Elongation</i>	kN/m	MD 20 (± 3,0) CMD 20 (± 3,0)	
Übliche Bezugskraft <i>Usual force at strain</i>	%	MD 59 (- 9,0) DIN EN CMD 60 (- 10,0) ISO 10319	
Flächengewicht <i>Mass per unit area</i>	kN/m	MD 11 (± 3,0) DIN EN CMD 12 (± 3,0) ISO 10319	
Rollenmasse <i>Roll dimensions</i>	g/m ²	@ 2% 3% 5% 10%	
Vorgesehene Funktion <i>Intended use</i>	kN/m	MD 11 13 17 38 CMD 10 12 15 32	
	g/m ²	380 (± 30) DIN EN ISO 9864	
	±10%	Breite Länge Gewicht <i>width</i> <i>length</i> <i>weight</i>	
	R	5,00 m 100 m 210 kg	
		Bewehrung von Erdbauwerken <i>Soil reinforcement</i> 	

Standard tolerances and technical developing change reserved
 The latest version of all Technical Data Sheets is available at www.synteen.de.